

Abstract of the Disclosure

A method of chemical vapor deposition (CVD) of copper films includes preparing a substrate, including forming structures thereon have a barrier metal exposed surface; placing the prepared substrate into a CVD chamber; heating the substrate to a temperature of between about 200°C and 250°C; introducing a water flow in a carrier gas for at least one minute; stopping the water flow; and starting the flow of copper precursor.

090944 104604  
103404 12482600